

# Test Report

GIN YUAN SENG ENTERPRISE CO., LTD.  
NO. 82, JIOW-BUH VILLAGE, HSING-YING CITY,  
TAIWAN COUNTRY, TAIWAN.

Report No: CY/2008/31344

Date: 2008/04/07

Page : 1 OF 3

**The following merchandise was submitted & identified by the client as:**

Type of Product: PP ZIEEPER LINE  
Manufacturer/Vendor: TAIWAN  
Date of Sample received: 2008/03/26

## **Test Requested:**

For compliance with EEC Directive on overall migration test of Plastic Material and Articles intended to come into contact with Foodstuffs (90/128/EEC) and Commission Directive 92/39/EEC (amendment of 90/128/EEC).

## **Test Method:**

As specified in EEC : (85/572/EEC) for simulant to be used; EEC : (82/711/EEC) for basic rules (testing conditions) necessary for testing migration of the constituents of plastic materials and articles intended to come into contact with foodstuffs and Commission Directive 93/8/EEC (amendment of 82/711/EEC), 97/48/EC (second amendment of 82/711/EEC) and EN 1186.

## **Test Results:**

Please refer to next page.

## **Conclusion:**

The submitted samples do comply with the requirements of overall migration test in the Directive on Plastic Materials and Articles intended to come into contact with Food stuff (90/128/EEC) and Commission Directive 97/48/EEC (amendment of 90/128/EEC) and 2005/79/EC (amendment of 2002/72/EC) for the specific simulant used (deionized water, 3% acetic acid aqueous solution, 10% ethanol aqueous solution and rectified olive oil)



James Lu / Supervisor

Signed for and on behalf of  
SGS TAIWAN LTD.

Chemical Laboratory – Taipei

# Test Report

GIN YUAN SENG ENTERPRISE CO., LTD.  
 NO. 82, JIOW-BUH VILLAGE, HSING-YING CITY,  
 TAIWAN COUNTRY, TAIWAN.

Report No: CY/2008/31344  
 Date: 2008/04/07  
 Page : 2 OF 3

## Test Results:

Overall migration test of plastic material and articles

Pass

<u>Simulant used</u>	<u>Overall Migration (mg/dm<sup>2</sup>)</u>	<u>Limit (mg/dm<sup>2</sup>)</u>
Deionized Water	7.4	10
3% Acetic Acid (W/V) Aqueous Solution	4.0	10
10% Ethanol (V/V) Aqueous Solution	5.2	10
Rectified Olive Oil	9.4	10

## Sample Description:

White plastic.

Note: Contact time : 4 hours < t ≤ 24 hours  
 Contact temperature : 20°C < Temp. ≤ 40°C  
 Test condition : 40°C, 24 hours  
 Testing period : 2008/03/27-04/07  
 < = Less than

## Test Report

GIN YUAN SENG ENTERPRISE CO., LTD.  
NO. 82, JIOW-BUH VILLAGE, HSING-YING CITY,  
TAIWAN COUNTRY, TAIWAN.

Report No: CY/2008/31344  
Date: 2008/04/07  
Page : 3 OF 3

